

SPIGOT & CHANNEL GROUT

SPECIALLY FORMULATED FOR THE GLASS INDUSTRY

RECOMMENDED
USES AS SHOWN

- | Spigot and channel fixing
- | Cementitious grouting where particular application requires rapid setting
- | Anchoring bolts, bars and fittings

SET TIMES

Polaris Spigot and Channel Grout has varying factors that effect the set time. All guides are estimated times only. Factors to consider when using; air temperature, water temperature, water volume, powder temperature and amount being mixed (larger amounts mixed will speed up the set time. Set times below are based on a air, water and powder temperature at 22 deg and the volume being mixed is 5kg

SET TIMES

30 - 40 Mins 10°
15 - 20 Mins 25°
10 - 15 Mins 35°
<10 Mins 35°+



*25 Min
Quick Set*

PROPERTIES

- Aggregate free
- Rapid strength gain facilitates for rapid installation
- Ready to use, pre-mixed, requires only the addition of water
- Can be mixed for stiff, plastic, flowable or fluid application
- Lower water/cement ratio reduces drying shrinkage, increases durability and reduces permeability
- Dual expansion compensates for shrinkage in the plastic and hardened state

2 x 10Kg Bags